DISTRIBUTION AND ECONOMIC POTENTIAL OF MANGANESE DEPOSITS IN NIGERIA: A REVIEW

3 Abstract

- The Northern basement complex of Nigeria contains a large number of manganese deposits. So 4 far, ten deposits of manganese have been reported by previous workers. These deposits occur 5 within Precambrian metasediments (schist belt), mafic and ultramafic rocks which are 6 Proterozoic in age and folded into synclinorial belts within the crystalline basement complex. 7 Considering their widespread distribution in space, time and tectonic setting, some are 8 considered to be of ensilalic mode of evolution while others are ensimatic. However, the 9 mineralizations are mostly of poor grade, and thus require beneficiation processing. The local 10 11 steel industries within the country have continued to depend on manganese ore. No satisfactory substitute for manganese in steel production has been identified as at present. The applications of 12 manganese deposits by geologists, chemical and environmental engineers, ceramicists, soil 13 14 scientists and microbiologists shows a bright future for manganese ore in Nigeria. The ever increasing demand for steel products has continued to put pressure on Federal Government of 15 Nigeria to complete the construction work at the nation's steel producing plant which, will result 16 17 in the need for a manganese concentrates for economic growth and development.
- 18 **KEYWORD:** Northern basement complex, schist belt, mineralizations, beneficiation, tectonic19 setting, concentrates.

20

21

1

2

INTRODUCTION

- The surface area of Nigeria 923,-768_sq.km is covered in nearly equal proportions by crystalline
- and sedimentary rocks (Rahaman, 1988). The Nigerian Basement Complex is characterized by

different grades of metamorphism, orogenies and structural modifications (Odeyemi, 1977; Ajibade *et al.*, 1987; Caby, 1989) and these have been reflected in its complex petrological, structural composition and mineralization potential. The younger metasediments in Nigeria are well known for their mineralization such as Ggold, Banded Iron Formation (BIF), lead / zinc ores, tantalite manganese deposits and marble are associated with them (Woakes, *et al.*, 1987; Dada *et al.*, 1989; Oyinloye, 2006). Nigeria has over 5,000,000 metric tons (MT) of manganese deposit (Ministry of Solid Minerals and Development - MSMD, 1997; Raw Material Research and Development Councils - RMRDC, 2009).

PREVIOUS WORKS

Nigeria is situated within the Pan–African mobile belt, which is a part of an Upper Proterozoic mobile belt, extending from Algeria across the Southern Sahara into Nigeria, Benin and Cameroon. The Pan- African belt continues into north-eastern Brazil, where manganese rocks are also known to occur (Truswell and Cope, 1963; Yaro, 1998). It is situated between the Archean- Paleoproterozoic blocks of West African Craton in the west, the Congo Craton in the south east and the east Sahara block in the northeast (Figure. 1). (Black, 1980). Figure 1).




Figure (1): Pre- drift Proterozoic belts and their Phanerozoic cover rocks between the Cratons (Dada, 2008)

The Northern basement complex of Nigeria contains a large number of manganese deposits. So far, ten deposits of manganese ore have been reported in various parts of the Nigeria where they are associated with the mafic and ultramafic complexes and metasediments of the basement complex (Truswell and Cope, 1963; RMRDC, 2009; Yaro, 1998; National Steel Raw Materials Exploration Agency - NSRMEA, 2010; Bamalli, *et al.*, 2011; Muriana *et al.*, 2014).

DISTRIBUTION OF MANGANESE DEPOSITS IN NIGERIA

The manganese occurrences of north western Nigeria have been variously reported. Wright and McCurry, (1970) worked on the manganese deposits at Mallam Ayuba within the Maru schist belt. They observed that the manganese mineralization occurs in ridges for over 800m along a north- south strike and lying near Mallam Ayuba settlement. The ore bodies composed of massives brown- gray-black, jointed or fractured, fine-grained iron manganese mineralization dipping at 85° east with strike direction of 110° (Bar and Mucke, 1982), having a conformable beds of quartzite that contains banded iron formation (BIF), gold and amphibolites (Moneme and Scott, 1983). The Tudun Kudu manganiferous ore occur within Precambrian metasediments (Karaukarau schist belt) which are Proterozoic rocks, folded into synclinorial belts within the crystalline basement complex, and metamorphosed to phyllites, quartzites and psammitic schists of low to medium grade (Moneme *et al.*, 1982; Mucke and Okujeni, 1984).


Available studies show that small quantities of manganese deposits have been reported from basement rocks in South-eastern and South-western parts of Nigeria (Raeburn, 1927; Bafor and Mucke 1990). However, the mineralizations are mostly of poor grade, and thus require some processing to improve quality for industrial uses. Table (1) gives the summary of the major manganese deposits occurrence in Nigeria (figure 2). Figure 2 showing a simplified geological map of Nigerian basement complex.

Table 1: Summary of occurrences and distribution of manganese deposits in various locations in Nigeria

S	State	Location	Grade	Estimated	References
				Reserve (Ton	
1	Niger	Madaka	-	Nd	Muriana <i>et al.</i> , (2016).
		Alawa,	Low		Truswell and Cope, (1963)
2	Edo	Igarra	-	Nd	Bafor and Mucke, (1990)
3	Adamawa	Mubi	Low	Nd	Vandi, (2014)

	4	Kebbi	Ka'oje.	Low	Nd	Muriana <i>et al.</i> , (2014)
			Wasagu/Danko	-	-	Binta, (2013), Binta et al.,
	5	Borno				(2016) RMRDC,(1999)
	<i>5</i>	Cross River	- Duoala	Low	- Nd	Raeburn, (1927)
	8	-Zamfara	Maikujeri, Darene	Low	-	NSRMEA, (2010),
•			Mallam Ayuba,	Low	Nd	Yaro,(1998)
	9	Kaduna	Birnin Gwari			Bamalli, et al., (2011)
						RMRDC. (1999)
						Moneme and Scott,
						(1983); Bar and
						Mucke,(1982);Wright and
						McCurry, (1970)
			Ugoge (S/W)	Low	-	Bartholomew, (1982).
			Ugoge (S/E)	Low	-	Widadason, (1982)

70 ND= Not Determined, - Unknown



72 Figure 2. Simplified geological map of Nigeria Basement Complex showing the schist belts

73 where manganese occurs (Modified after Woake et al., 1987 and Danbatta, 2008).

74

96

ECONOMIC POTENTIAL OF MANGANESE IN NIGERIA

75 The use of manganese in steel production is a double-edged sword, as the metals fortune is 76 77 intimately tied to the steel industry. Hence, the need to develop a simple and practicable route for the processing and extraction of manganese from its ores is necessary. The use of Manganese 78 in dyes, paints, battery cells, glass and textiles industries is also of great importance. 79 In Nigeria, for instance, the per capital consumption of steel is very low. About 10 kg or less is 80 the index used to determine the level of industrialization of a country. Statistics showed that 81 Nigeria is lagging behind; and other countries with lesser endowments like Zimbabwe (25 kg), 82 Egypt (42 kg), Algeria (38 kg) and South Africa (112 kg), are ahead of Nigeria in terms of steel 83 production and consumption (Bamalli et al., 2011). 84 (1) Steel processing: The various end-uses of manganese have different ore requirements giving 85 rise to the classification of manganese ore into metallurgical, chemical and non-metallurgical 86 grades. The biggest use of manganese is for the production of steel and cast iron (Yaro, 1998; 87 88 Muriana et al., 2014) Manganese has two important properties in steelmaking: its ability to 89 combine with sulphur to form Aalabandite (MnS) and its deoxidation capacity (Imer, 1997). (2) As alloy: Binta, (2013) reported that about 94% of the manganese ore is converted into 90 91 manganese alloy, These are used in production of stainless steel, heat resistant steel and electric welding electrodes, and as an alloying element in steel where it improves the strength, toughness, 92 hardenability, workability, abrasion resistance of steel and electrical conductors. 93 (3) Environmental uses: Mn oxides have been used for many different applications in water and 94 waste water treatment as deoxidizer; soil and sediment remediation (of metals and organics); For 95

example, a widely used filtration medium for drinking water is manganese greensand (glauconite

- 97 with Mn oxides of various Mn valence states), designed specifically to remove Mn(II), Fe(II),
- hydrogen sulfide, and arsenic (Mucke 2005). 98
- (4) It serves as catalysts and adsorbents in the laboratory: The oxidation of Mn²⁺ to Mn³⁺ and 99
- Mn⁴⁺ is largely catalyzed by micro organisms and greatly accelerates the rate of oxidation in 100
- many environments. Owing to the high activation energy, the oxidations of Mn²⁺ act as 101
- 102 adsorbents in the laboratory.

CONCLUSION

103

- Previous workers like (Truswell and Cope, 1963; Mucke and Bafor, 1990; RMRDC, 2009; 104
- Yaro, 1998; Bamalli et al., 2011; Muriana et al., 2014, and Muriana et al., 2016) revealed that 105
- 106 manganese deposit reserves exist in Nigeria, which have potentials as raw materials for industrial
- applications such as batteries, steel and electrical appliances. The present level of exploitation is, 107
- however, very low and in most cases, appropriate processing would be necessary to attain 108
- desirable qualities. 109

REFERENCE

111

110

115

118

125

- 112 Ajibade, A.C., Woakes, M., and Rahaman, M.A., (1987). Proterozoic crustal development in the Pan-African regime of Nigeria. In: A. Krooner (Editor), Proterozoic crustal evolution
- 113
- Geodynamic Services American Geophysics union 17, pp. 259 271. 114
- Bamalli, U. S, Ali, M., and Mohammed, S.C., (2011). A review of Nigerian metallic minerals for 116 technological development, *Natural Resources* 2, pp. 87 – 91. 117
- Bar, P. and Mucke, A. (1982). Mineralisation and genesis einiger Nigerian ischer manganv 119 rkornrncn (Tudun Kudu Hill, Ungwan Malam Ayuba, bei Gangara, Ruwan Doruwa and 120
- Maraba Hill). *Fortschr* 1, pp. 148 149. 121 122
- Bafor, B. E and Mucke, A., (1990). The genesis of manganese concretions in the Igarra area, 123 Southwestern Nigeria. Journal of African Earth Sciences 10, pp. 595 - 601. 124
- Bartholomew, A., (1982). The geology and geochemical secondary dispersion pattern of 126 manganese occurrence in Ugoge via Giwa, Kaduna State, Nigeria. Unpublished B.Sc 127 Thesis, Ahmadu Bello University, Zaria, Nigeria. 61pp. 128

- Binta, H., (2013). Upgrading of Wasagu manganese ore to metallurgical grade concentrate, Unpublished M.Sc Thesis, Ahmadu Bello University, Zaria, 66pp.
- Binta, H., Yaro, S.A., Thomas, D.G., and Dodo., M.R., (2016). Beneficiation of low grade mangansese ore from Wasagu, *Journal of Raw Materials and Development* 10 (2). pp. 45-51
- Black, R., (1980). Precambrian of West Africa, *Episodes* 4: pp. 3–8.

132

136

138

141

144

148

151

154

158

162

165

168

- Caby, R., (1989). Precambrian terranes of Benin-Nigeria and Northeast Brazil and the Late proterozoic South Atlantic fit, *American Spectrum Paper* 230, pp. 145 158.
- Dada, S. S., (2008). Crust-forming ages and Proterozoic crustal-evolution in Nigeria. *Geoscience Letters* 2. pp. 5-11
- Dada, S. S., Birck, J. L. and Rahaman, M. A., (1989). Archean Migmatite Gneiss Complex of
 North-central Nigeria: Its geochemistry and evolution. *International colloquium on African Geology*, Mbabane Swaziland 1, pp. 97-102.
- Danbatta, U. A., (2008). A review of the evolution and tectonic setting framework of the schist belts, Northwestern, Nigeria. *Journal of science*, pp. 24-35
- McCurry, P., (1970). The geology of Sheet 21, Zaria Unpublished M.Sc thesis, Ahmadu Bello University, Zaria
- Moneme, P. C., and Scott, P. W., (1983). The mineralogy of Malam Ayuba manganese
 mineralization in Maska, Sheet (101). Nigerian Mining Geosciences Society 19th Annual
 Conference, Warri. pp. 23 -24.
- Moneme, P. C; Scott, P. W; and Dunham, A. C., (1982). Occurrence of manganese ores in Zaria
 Area, Kaduna State. *Nigerian Mining Geosciences Society Abstracts*, 18th Annual
 Conference, Kaduna. pp. 17-18.
- MSMD, (1997). Ministry of Solid Minerals and Development: An Inventory of solid minerals in Nigeria. *Geological Survey of Nigeria* Press. 59pp.
- Mucke, A, (2005). The Nigerian manganese –rich iron formation and their host rocks- from sedimentation to metamorphism, *Journal of Africa Earth Sciences* 41, pp.407 436.
- Mucke, A. and Okujeni, C., (1984). Geological and ore microscopic evidence on the epigenetic origin of the manganese occurrences in Northern Nigeria. *Journal of Africa Earth Sciences* 3, pp. 209 225.
- Muriana, R. A,. (2016). Discharge evaluation of battery-active chemical manganese dioxide produced from Madaka (Nigeria) manganese ore. *Journal of Engineering Research* 20, pp. 67-78.

- Muriana, R. A., Muzenda. E. and Abubakre, O. K., (2014). Extraction and production kinetics of
 industrial grade manganese sulphate crystal from manganese. *Journal of Engineering Research* 19, pp.78 90.
- NSRMEA, (2010). National Steel Raw Materials Exploration Agency, geological report on manganese deposit in Kaoje Bungudu, *Issue* 3, pp. 45 -58.
- Odeyemi, I. B., (1977): Late -Proterozonic metconglomerates in the Schist Belt of Nigeria: origin and tectonostratigraphic significance revisited. *Journal of technoscience* 3 pp. 48-55.
- Oyinloye, A.O., (2006). Geology and geochemistry of some crystalline basement rocks in Ilesha area Sourthwestern Nigeria: Implications on provenance and evolution. *Journal of Science India Research*, 50, pp. 223-231.
- Rahaman, M. A., (1988). Recent advances in the study of the basement complex of Nigeria. In:
 Precambrian Geology of Nigeria. *Geological Survey of Nigeria*. pp. 11-14
- 194 Raeburn, C., (1927). Tinstone in Calabar. *Bulletin of Geological Survey of Nigeria* 11, pp. 72-88.
- 196 RMRDC, (2009). Non Metallic in Nigeria: *Raw Material Research and Development Councils*, 197 *Abuja*, 13p.
- Truswell, J. F., and Cope, R.N., (1963). The geology of parts of Niger and Zaria provinces, northern Nigeria. *Bulletin of Geological Survey Nigeria* 29, pp. 34 48.
- Vandi, D. K., (2014). Geology and geochemistry of manganese ores in Mujara, Mubi South, Northeast Nigeria, B.Sc Thesis Modibbo Adamawa University of Technology, Yola. 32pp.
- Widadason, G. A., (1982). The geology and geochemical secondary dispersion pattern of the manganese occurrence at Ugoge (Tudun Kudu) Southeastern sector, Department of Geology, Ahmadu Bello University, Zaria, Nigeria (unpublished). 67pp.
- Woakes, M., Ajibade C.A., and Rahaman, M.A., (1987). Some metallogenic features of the Nigerian Basement Complex, *Journal of Africa Science* **5**. Pp. 655-666.
- Wright, J. B., and McCurry, P., (1977). First occurrence of manganese ores in northern Nigeria.
 Economic Geology 65, pp. 103 106.
- Yaro, S. A., (1998). Development of a process route for the beneficiation of Mallam Ayuba manganese deposit to ferromanganese feed grade. Unpublished Ph.D. Thesis, Ahmadu Bello University, Zaria, 79pp.

219

179

182

186

190

193

198

205

209

212