




Comparative study of coconut cellulose against Avicel 102.

Carr's Index (%) Cellulose (%)	Powder flow rate (g/s)			Angle of repose				
	MCCF	MCCL	AVC-102	MCCF	MCCL	AVC-102		
100	11.15	13.35	13.16	5.33	5.27	26.96	35.24	27.95
80	10.61	15.22	10.26	5.54	2.2	6.1	28.15	33.51
70	11.59	14.89	13.35	6.23	2.58	6.45	29.3	31.05
60	9.86	12.5	13.04	6.25	3.02	6.57	29.8	30.83



Friability (%)

Cellulose (%)	MCCF (%)	MCCL (%)	AVC-102 (%)
100	0.5	0.18	0.56
80	0.92	0.67	0.85
70	1.43	0.98	0.87
60	4.12	1.12	1.02

