

1     **A COMPARATIVE STUDY OF COPPER, ZINC AND ALUMINIUM AS**  
2     **ELECTRODES IN THE PREPARATION OF STARCH-BASED**  
3     **POLYELECTROLYTE**  
4  
5  
6

6                                     **ABSTRACT**

7     **Alum ( $\text{Al}_2(\text{SO}_4)_3 \cdot 18\text{H}_2\text{O}$ ) has been the coagulant mostly used in water treatment process.**  
8     **Alum imported into the country gets stuck at the port because of the congestion of the**  
9     **port. When alum is used to coagulate water, it depresses the pH of the water, thus,**  
10    **requiring a pH booster. Because of the high dependence on alum, alternative coagulants**  
11    **produced with local raw materials will be of great advantage. A starch-based**  
12    **polyelectrolyte was prepared by dispersing 3 g of cassava starch and 10 g of heaping**  
13    **teaspoon of high-test granular calcium hypochlorite (commercially available as HTH) in**  
14    **100 ml distilled water; making it up to a litre solution with hot distilled water (temperature**  
15     **$80^\circ\text{C} - 100^\circ\text{C}$ ) and electrolysing by means of stabilized power supply using aluminium**  
16    **rods as electrodes to produce polyelectrolyte A. Copper rods and zinc rods were**  
17    **similarly used to polyelectrolyte B and polyelectrolyte C respectively. To test the effect(s)**  
18    **and interaction of the charging variables, i.e. separating distance, power supply and time**  
19    **of charging, a three-factor experiment ( $2^3$  factorial design) was carried out. The variables**  
20    **were operated at High Level (+) and Low Level (-). The analysis indicate that the power of**  
21    **charging has the most significant effect on the coagulation characteristics of the starch-**  
22    **based polyelectrolyte. Polyelectrolytes A and C were tested with raw water drawn from**  
23    **Opa dam and were found to be effective water coagulants. Polyelectrolyte B on the other**  
24    **hand, adds to the turbidity of the raw water with which it was tested. Polyelectrolyte A**  
25    **was found to be as effective as Alum at natural water condition (pH 7) causing better**  
26    **than 88% turbidity removal with dosage of 65 mg/l.**

27  
28    **Keywords: Comparative, Starch-based polyelectrolyte, alum, coagulant, surface water**  
29    **treatment.**  
30

31    **1. INTRODUCTION**

32    Water which is absolutely pure is not found in nature, every water vapour condensing in air contains solid  
33    and dissolved gases. As condensed water falls it sweeps up other material from the air and becomes  
34    contaminated on reaching the ground, running over the surface and percolating through the various strata  
35    of the soil [1]. These contaminants may be removed by passage through the soil as a result of filtration  
36    and exchange and adsorption reactions; some may be removed from the surface water by sedimentation  
37    and biological activity; others may be removed by specific engineered process in water treatment plants.  
38    New impurities are introduced by dissolution and exchange reactions in the soil, others by accumulation  
39    of decomposition and reactions with the materials of the distribution system [2]. In order to provide a  
40    potable water supply, raw water from the source has to be treated. The source may be a river, reservoir,  
41    well or natural lake. Each of these sources have their own peculiar impurities and means of removing

42 them. A large portion of the suspended particles in water are sufficiently small that their removal in the  
43 sedimentation tank is impossible at reasonable surface overflow rate [3]. Coagulation is also called  
44 chemically assisted sedimentation; it is the process of causing the finely divided particles in water to  
45 cluster together and form larger particles (flocs) and later settle before passing the water to the filter [4].  
46 The four major mechanisms of coagulation are double-layer compression, adsorption and charge  
47 neutralisation, enmeshment in a precipitate and adsorption by polymers, and inter-particle bridging. The  
48 understanding of the four processes is necessary for understanding the phenomena of coagulation [5].  
49 The coagulation unit is essential in removal of impurities and alum (aluminium sulphate) is the most  
50 common coagulating agent. There is a need for a local substitute due to the rapid increase in the number  
51 of water treatment plant and the constantly increasing cost of alum. Cationic starches have long been  
52 used to flocculate negatively charged particles from aqueous suspension. Safi *et al.* [6] reported the  
53 preparation of 2-aminoethyl ether derivatives of starch which readily flocculated aqueous suspensions of  
54 negative colloids. Salim *et al.*[7] reported the use of high molecular weight polyamines, polyalkylamines  
55 and polyacrylonitriles as flocculating materials. Cationic quaternary ammonium starch ether which was  
56 found to be an excellent flocculant for materials in aqueous system [8].  
57 Though these starches are effective flocculating agents for aqueous suspension of negatively charged  
58 inorganic and organic particle. Their precise modes of operation were not precisely understood. Sirin [9]  
59 was able to give a simple explanation, the simple ionic attraction between the product formed and the  
60 colloidal particles leading to the production flocculants – particle aggregates large enough to settle from  
61 suspension; the polyelectrolyte, according to his discovery also form bridge structure that leads to  
62 precipitation. Tenney *et al.* [10] explained that many of the suspended particles in raw water are too small  
63 to settle out by themselves in a separation by sedimentation process. The benefit of adding of polymer is  
64 derived from the agglomeration of these individual particles into larger clumps or flocs allowing them to  
65 settle and be removed. The list of synthetic polymers which have been successfully applied to treatment  
66 of water.

67

## 68 2. MATERIALS AND METHODS

69 Locally purchased cassava was peeled and washed. They were then crushed, with a cassava grater  
 70 machine, then oaked for some time in water after which they were sieved. The filtrate was allowed to  
 71 settle for some hours and the settled starch was separated from the water by careful decantation of the  
 72 top water. The residue was then air dried, grounded and stored in a desiccator to prevent the adsorption  
 73 of water vapour from the atmosphere. The material obtained from this process was then used in the  
 74 preparation of the starch-based polyelectrolyte.

Comment [H1]: Please describe the grater

## 75 2.1. Preparation of Starch-based Polyelectrolyte

76  
 77 Tablets of calcium hypochlorite ( $\text{Ca}(\text{OCl})_2$ ), commercially available as HTH, were ground and stored in a  
 78 desiccator [11]. Three gram of starch and 10 g of hypochlorite were made into a well-mixed slurry with  
 79 100 ml distilled water in a one-litre beaker. Hot distilled water ( $70^\circ\text{C} - 100^\circ\text{C}$ ) was added to the slurry,  
 80 making it up to a litre solution with continuous stirring. The resulting solution was electrolysed on a  
 81 stabilized power supply with aluminium rods, copper rods and zinc rods as electrodes one after the other,  
 82 to produce polyelectrolytes A, B and C respectively. The solution was gently stirred in each case  
 83 throughout the process of charging. The variables i.e. power, P, separating distance, D and time of  
 84 charging, T; were tested at the high level (+) and low level (-) for each of the electrodes to generate a  $2^3$   
 85 factorial runs for each of the electrodes (Tables 1 and 2).

86

87 **Table 1: Electrolysing Variables Values at High and Low Levels**

Variable	High Level (+)	Low Level (-)
Power product of voltage and current (watts)	400	100
Separating distance (mm)	150	50
Time of charging (min)	60	30

88

89

90

91 **Table 2: Factorial Design Table**

Run	1	2	3	4	5	6	7	8
Power, P (Watts)	-	+	-	+	-	+	-	+

Separating Distance, D (mm)	-	-	+	+	-	-	+	+
Time, T (mins)	-	-	-	-	+	+	+	+

92

93 **2.2. Coagulation of Water Samples**

94 Raw water from the university dam, Opa Dam, was collected and used in testing the effectiveness of the  
95 starch-based polyelectrolyte as a coagulant under neutral condition i.e. natural water, pH 7.

96 Treatment in each case consisted of dosing varying amount of the prepared polyelectrolyte into the water,  
97 mixing rapidly for 60 seconds and then slowly for 10 minutes in a jar test stirrer. The water was then  
98 allowed to settle for 30 minutes. Coagulation effectiveness was determined by measuring turbidity of the  
99 water sample before and after treatment using a Hach's Model 2100A turbidimeter.

100

101

102 **3. RESULTS AND DISCUSSION**

103 Preliminary coagulation test carried out with the starch-based polyelectrolyte as coagulant revealed the  
104 following: the ratio of hypochlorite to starch must not be less than 3; the polyelectrolyte can be stored at  
105 room temperature for more than 12 days without materially losing its effectiveness as a coagulant; a  
106 better turbidity removal can be achieved if the settling time is increased; and when water at natural pH  
107 and temperature was used to make the slurry to a litre solution without stirring, the turbidity removal is  
108 relatively low compared with when hot distilled water is used with continuous agitation [12].

109 **3.1. Comparing the Effectiveness of the Polyelectrolytes**

110 Varying amounts, in millilitres, of the polyelectrolytes were used to treat litres of raw water sample  
111 (turbidity, 28 NTU). Table 3 shows the conversion from millilitre to milligrams per litre; the conversion is on  
112 the basis that 1 mg/l of the solution prepared as indicated in the preceding contain 3 mg/l of starch and 10  
113 mg/l of hypochlorite and that when 1 ml is dosed into a litre of water sample, the dosage is 3 mg/l  
114 expressed in term of combination of hypochlorite and starch (i.e. in terms of polyelectrolytes itself).

115 **Table 3: Expression of Polyelectrolyte (ml) in terms of Dosage (mg/l)**

Volume of coagulant per litre (ml)	Polyelectrolyte expressed as		
	Starch (mg/l)	Hypochlorite (mg/l)	Polyelectrolyte (mg/l)
0	0	0	0
2.5	7.5	25.0	32.5
5.0	15.0	50.0	65.0
7.5	22.5	75.0	97.5
10.0	30.0	100.0	130.0
12.5	62.5	125.0	187.5
15.0	75.0	150.0	225.0

116

117 Table 4 shows the relative performance of varying dosages of polyelectrolytes A, B and C under neutral  
 118 condition. The performance of polyelectrolyte A is generally better than those of B and C at neutral pH.  
 119 Polyelectrolyte B on the other hand, increases the turbidity of the water with which it was tested. The  
 120 percentage turbidity removals were computed based on Table 4 for polyelectrolytes A, B and C for each  
 121 experimental run. Table 5 shows that polyelectrolyte A at pH 7 performs generally better than  
 122 polyelectrolytes B and C.

123

124

125

126

127

128

129

130

131

132 **Table 4: Relative effects of varying dosages of polyelectrolytes A, B and C on turbidity**  
 133 **removal and pH of treated water samples**

Dosage	Polyelectrolyte C	Polyelectrolyte B	Polyelectrolyte A
--------	-------------------	-------------------	-------------------

(mg/l)	Final turbidity (NTU)	Final pH	Final turbidity (NTU)	Final pH	Final turbidity (NTU)	Final pH
0						
15	13.2	7.8	42.2	7.6	6.2	7.7
32.5	11.6	7.7	43.4	7.6	4.8	7.7
65	9.8	7.6	44.0	7.5	3.8	7.5
97.5	10.0	7.4	44.0	7.4	4.2	7.4
130	12.4	7.3	44.7	7.4	5.6	7.4

134

135 Table 5: Summary of Percentage Turbidity Removal of Polyelectrolytes A, B and C

Dosage (mg/l)	Percentage Turbidity Removal		
	Polyelectrolyte A	Polyelectrolyte B	Polyelectrolyte C
130	63.52	-18.26	45.48
97.5	70.39	-17.8	50.15
65	74.8	-16.44	52.68
32.5	70.48	-14.46	49.08
15	59.75	-12.95	43.84

136

137

138

139

140

### 141 3.2. Main Effect and Interaction of Charging Variables by Factorial Analysis

142 The main and interaction effect(s) were used to determine the level of influence the factors had on one  
 143 another and how the influence was occurring (Uduman *et al.*, 2010). Table 6 shows the summary of this

144 results. It can be seen that power had the most significant main effect on the coagulation characteristics  
145 of the starch-based polyelectrolyte while the highest level of interaction effect was observed between the  
146 separating distance and the time of charging.

147

148 **Table 5: Summary of main effect and interaction effect of the charging variables**

Effect	Polyelectrolyte A	Polyelectrolyte B	Polyelectrolyte C
Mean	74.75	27.98	52.63
P	19.0	-21.07	17.25
D	-0.5	8.43	1.25
PD	0	2.17	-1.75
T	1.0	5.97	1.25
PT	-3.5	-3.68	4.25
DT	-7.0	1.98	-8.75
PDT	2.5	-12.03	-0.75

149

150

#### 151 **4. CONCLUSION**

152 Based on the results, the following conclusions could be drawn: when 3 g of cassava starch and 10 g of  
153 calcium hypochlorite are dispersed in hot distilled water and charged, the resulting product, starch-based  
154 polyelectrolyte, is effective in coagulating raw water. A dosage of 65 mg/l of polyelectrolytes A and C  
155 result in 88% and 69% turbidity removal respectively. The same dosage of polyelectrolyte results in 7.5%  
156 turbidity addition.

157 Polyelectrolyte A performs generally as well as alum but does not depress the pH as alum does. This  
158 means that the starch-based polyelectrolyte needs little or no lime to aid it in the reduction of potable  
159 water at the neutral pH range. The solution is stable at room temperature. it neither spoils nor loses its  
160 coagulation effectiveness for at least 12 days. Power supplied during the charging process has the most  
161 significant effect on the coagulation characteristics of the starch-based polyelectrolyte while the highest  
162 level of interaction effect is between separating distance and time of charging.

163 REFERENCES

- 164 [1] Gerde J. A., Yao, L. X., Lio, J. Y., Wen, Z. Y. & Wang, T. (2014). Microalgae flocculation:  
165 Impact of flocculant type, algae species and cell concentration. *Algal Research-Biomass*  
166 *Biofuels and Bioproducts* **3**, 30-35.  
167
- 168 [2] Ellis, A.E., Stanley, I.U., Abiola, O. and Ogedengbe, M.O. (1981). "Preparation of cationic  
169 starches as flocculants for water." *Water Resources*. Vol. 16, pp. 1433 – 1435.  
170
- 171 [3] Granados, M. R., Acien, F. G., Gomez, C., Fernandez-Sevilla, J. M. & Grima, E. M. (2012).  
172 Evaluation of flocculants for the recovery of freshwater microalgae. *Bioresource Technology*  
173 **118**, 102-110.  
174
- 175 [4] Lee, A. K., Lewis, D. M. & Ashman, P. J. (2014). Microbial flocculation, a potentially low-  
176 cost harvesting technique for marine microalgae for the production of biodiesel. *Journal of*  
177 *Applied Phycology* **21**, 559-567.  
178
- 179 [5] Rashid N., Rehman, S. U. & Han, J. I. (2013). Rapid harvesting of freshwater microalgae using  
180 chitosan. *Process Biochemistry* **48**, 1107-1110.  
181
- 182 [6] Safi C., Zebib, B., Merah, O., Pontalier, P. Y. & Vaca-Garcia, C. (2014). Morphology,  
183 composition, production, processing and applications of *Chlorella vulgaris*: A review.  
184 *Renewable & Sustainable Energy Reviews* **35**, 265-278.  
185
- 186 [7] Salim S., Bosma, R., Vermue, M. H. & Wijffels, R. H. (2011). Harvesting of microalgae by  
187 bioflocculation. *Journal of Applied Phycology* **23**, 849-855.  
188
- 189 [8] Sanchez J. F., Fernandez, J. M., Acien, F. G., Rueda, A., Perez-Parra, J. & Molina, E. (2008).  
190 Influence of culture conditions on the productivity and lutein content of the new strain  
191 *Scenedesmus almeriensis*. *Process Biochemistry* **43**, 398-405.  
192
- 193 [9] Sirin, S. (2012). Harvesting the microalgae *Phaeodactylum tricornutum* with polyaluminum  
194 chloride, aluminium sulphate, chitosan and alkalinity-induced flocculation. *Journal of Applied*  
195 *Phycology* **24**, 1067-1080.  
196
- 197 [10] Tenney M. W., Echelber, Wf, Schuessl, Rg & Pavoni, J. L. (1969). Algal flocculation with  
198 synthetic organic polyelectrolytes. *Applied Microbiology* **18**, 965-&.  
199
- 200 [11] Uduman N., Bourniquel, V., Danquah, M. K. & Hoadley, A. F. A. (2011). A parametric study  
201 of electrocoagulation as a recovery process of marine microalgae for biodiesel production.  
202 *Chemical Engineering Journal* **174**, 249-257.  
203
- 204 [12] Vandamme D., Foubert, I., Fraeye, I., Meesschaert, B. & Muylaert, K. (2012). Flocculation  
205 of *Chlorella vulgaris* induced by high pH: Role of magnesium and calcium and practical  
206 implications. *Bioresource Technology* **105**, 114-119.  
207