

## Original Research Article

### AXIAL AND RADIAL VARIATION OF FIBRE CHARACTERISTICS OF *Bambusa vulgaris*

#### ABSTRACT

This study was carried out to investigate the axial and radial variation of fibre characteristics of *Bambusa vulgaris*. There were eighteen treatments for both axial and radial variation. The treatments were replicated three (3) times, in Complete Randomized Design (CRD). This Study was carried out at the Wood Anatomy Section of the Department of Forest Product Development and Utilization, Forestry Research Institute of Nigeria, Ibadan between July and August, 2018. Three (3) stands of *B. vulgaris* stands were randomly selected. Samples were cut into 10 cm discs collected at 25%, 50% and 75% of the total height (Axial positioning) of the bamboo stems. The samples discs were partitioned into two zones which are core and peripheral (bark) layers. From each of the disc, 3 slivers were obtained both from radial and axial positions. Slivers obtained were macerated with an equal volume (1:1) of 10% glacial Acetic acid and 30% Hydrogen Peroxide (H<sub>2</sub>O<sub>2</sub>) at 100 ± 2 °C. The resulting image on light microscope screen was measured for fibre length, fibre diameter and lumen width.

At 50% sampling height and at outer layer, the highest fibre length of 3.25 mm, followed by 3.06 mm of bamboo stand three (3) while the least 2.28 mm was recorded in stands two (2) of 75% axial positioning and at peripheral layer. The lumen width ranged between 3.52 × 10<sup>-3</sup> μm to 4.46 × 10<sup>-3</sup> μm in the radial direction from the core to the peripheral (bark) of the bamboo. The result obtained for mean values of Fiber diameter along the bamboo height ranged from 3.53 × 10<sup>-3</sup> μm to 4.46 × 10<sup>-3</sup> μm across the three (3) bamboo stands, sampling height and radial direction sampling respectively.

Comment [a1]: Space before units

26 Among the fibre positioning, the fibre collected from 50% of the sampling height have higher  
27 fibre diameter, lumen width and fibre diameter at the peripheral region compare to others.

28 **KEYWORDS:** *Bambusa vulgaris*, Fibre length, Fibre diameter and Lumen width.

29

### 30 **INTRODUCTION**

31 Fibre characteristics are related to many structural, physical and chemical properties of wood. The fibre  
32 characteristics includes fibre diameter, fibre length and lumen width. It affects many woody-product  
33 manufacturing, like pulping process, behavior in the drying process and resistance to cutting and  
34 machining, variations in fibre dimensions/characteristics are also present in the tree's radial, longitudinal  
35 direction and within the annual rings (Zobel and Van Buijtenen, 1989). The variation may be due to  
36 genetic, physiological or silvicultural treatment

37 In general, fibers can be classified into three categories: wood, non-wood, and non-plant. The term "non-  
38 wood" was coined to distinguish plant fibers from the two main sources of wood fibers; Hardwoods and  
39 softwoods. Non-wood or agro-based fibers are derived from selected tissues of various mono or  
40 dicotyledonous plants and are categorized botanically as grass, bast, leaf, or fruit fibers. Some non-wood  
41 fibers are classified by means of production; fibers such as sugar cane bagasse, wheat straw and corn  
42 stalks are byproducts. Other non wood fibers are grouped as "fiber plants," plants with high cellulose  
43 content that are cultivated primarily for the sake of their fibers such as jute, kenaf, flax, cotton, and ramie.  
44 Non-wood fibers can be used to make paper, although the quality varies a great deal depending on the  
45 source of the fibers.

46 *Bambusa vulgaris* (bamboo) has been one of the fastest growing plants in the world. Bamboo has social,  
47 economic and cultural significance and is used extensively for building materials along with thousands of  
48 uses. It is highly versatile raw material for different works. The bamboo is light weight, flexible, tough, high  
49 tensile, cheap material than the other building materials like steel. Bamboo can be used in various  
50 building works. Bamboo structures are reported to be to be flexible, earthquake resistant, light weight and  
51 cheap. Bamboo can be used as reinforcement in various structural members. Bamboo is a green material  
52 for sustainable development and has various advantages. Use of bamboo may be promoted for green  
53 buildings and sustainable development (Dinesh *et al.*, 2014). In fact, bamboo culture has been described  
54 as an essential part of human history and civilization, especially in Asia (Lobovikov *et al.*, 2007).

55 In addition, bamboo is used for scaffolding in construction projects often to great heights. While bamboo  
56 continues to be used in these traditional ways, it has also become an important raw material for  
57 production of modern building products (Bowyer *et al.*, 2014)  
58 Fibres have been regarded as one of the main components that determine the mechanical properties of  
59 any woody materials including bamboo owing to their unidirectional arrangement in the tissue as well as  
60 their unique cell wall structure (Gritsch *et al.*, 2004). Many study have been done regarding bamboo;  
61 Fibre wall anatomy (Parameswaran and Liese), and in particular cell wall thickening (Gritsch *et al.*, 2004;  
62 Murphy and Alvin, 1997) lignification (Itoh, 1990; Lybeer and Koch, 2005) and cell wall nano-structural  
63 changes (Suzuki and Itoh, 2001) during development of bamboo culms, mechanical properties of fibres or  
64 fibre caps (Zou, *et al.*, 2009 and Yu, *et al.*, 2011), and the underlying structure–property relationships of  
65 bamboo fibres that establish the gradients across the fibre caps have been intensively studied, but there  
66 has been little information on fibre characteristics variation along axial (top, middle and base) and radial  
67 (back and core) dimension in relations to its pulping potentials. Therefore, this study sought to provide  
68 input in this regards so as to provide information on variations across (radial) and along (axial) axis of *B.*  
69 *vulgaris*.

70

## 71 **MATERIALS AND METHODS**

### 72 **Materials**

73 The materials used for determining the variation in the fibre characteristics of *B. vulgaris* from the same  
74 location are; *Bamboosa vulgaris* samples, test tubes, tube rack, acetic acid (CH<sub>3</sub>COOH), Hydrogen  
75 peroxide (H<sub>2</sub>O<sub>2</sub>), Spatula, Beaker, Distilled water, Light microscope, saw, sharp knife, nose cover and  
76 hand glove.

### 77 **Sample Area**

78 The *B. vulgaris* stands used for this experiment was collected from Forestry Research Institute of Nigeria  
79 (FRIN), Ibadan, Oyo State. The institute is lies between Latitude 07°22'N and Longitude 03°58'E (Map of  
80 the World, 2017) of the Greenwich meridian. It is characterized by mean annual rainfall of 1400-1500\_mm,  
81 while the mean annual temperature is 26.46\_°C. The average relative humidity is 80-85% (FRIN, 2017).

82

83 **Experimental Site**

84 The experiment was carried out at Wood Anatomy laboratory, Department of Forest Products  
85 Development and Utilization (FPD&U), Forestry Research Institute of Nigeria, Ibadan (FRIN).

86 **Sampling Technique**

87 For this study, three (3) stands of *Bambusa vulgaris* stands were randomly selected from the bamboo  
88 plantation, behind horticultural nursery, Forestry Research Institute of Nigeria, Ibadan (FRIN) and  
89 harvested. Samples were cut into 10\_cm discs collected at 25%, 50% and 75% of the total height (Axial  
90 positioning) of the bamboo stems. The samples discs were later partitioned into two zones (radial  
91 positioning) which are core and peripheral (bark) layers.

92  
93 **Sample Preparation**

94 *B. vulgaris* (bamboo) collected were cut into 10\_cm discs collected at 25%, 50% and 75% (which  
95 represent base, middle and top of each stands respectively) of the total height (axial positioning) of the  
96 bamboo stems, from each of the disc, 3 slivers were obtained both from radial positioning (Core and  
97 peripheral layers) from each bamboo stem replicated three (3) times totaling 54 fibres used for this study.  
98 Bamboo slivers obtained were put into test tubes and macerated with an equal volume (1:1) of 10%  
99 glacial acetic acid and 30% Hydrogen Peroxide ( $H_2O_2$ ) at  $100 \pm 2$  °C and boiled until soft and bleached  
100 white as adopted by Franklin, 1945. The slivers were then washed, placed in 30\_ml\_-test tubes with 20\_ml-  
101 distilled water and shaken vigorously to separate the fibre bundles into individual fibre. The macerated  
102 fibre suspension was carefully aligned on a slide using white tread. The resulting image on light  
103 microscope screen was measured for fibre length, fibre diameter and lumen width.

Formatted: Subscript

Formatted: Subscript

104 **Microscopy**

105 The separated fibres per samples in each test tube were mounted on microscope slide and examined  
106 under a microscope with a tracer reflector. The magnified and transparent fibres were projected by the  
107 tracer reflector on which the fibres were viewed and traced under magnification  $\times 10$ . Few fibres were  
108 measured with calibration on the eye piece.

109 **Parameters Determined**

110 The parameters determined using the microscope is stated below.

- 111 • **Fibre length of the sample:** It was measured using the microscope by aligning fibre length of the  
112 chip sideways to the graduated ruler in the microscope.
- 113 • **Fibre diameter-width of the sample:** this was measured by placing the graduated ruler in the  
114 microscope in horizontal direction at the middle of the fibre.
- 115 • **Lumen width of the sample:** This is the width of the inner space.

#### 116 Experimental Design

117 The experiment was laid out in a Completely Randomized Design (CRD). There were 18 treatments  
118 randomly allocated with each treatment replicated 3 times making 54 observations.

#### 119 Data analysis

120 The data collected were analyzed using  $3 \times 3 \times 2$  factorial experiments in a Completely Randomized  
121 Design (CRD) replicated 3 times making 54 observations. The data gotten from the experiment was  
122 subjected to Analysis of Variance (ANOVA). The follow up test was conducted to know the difference  
123 between the means using the Duncan Multiple Range Test (DMRT) at 5% probability levels.

### 124 RESULTS AND DISCUSSION

#### 125 Fibre Length of *Bambusa-B. vulgaris*

126 The mean fibre length was presented in Table 1. The longest fibre length of  $3.25 \pm 0.15$  mm was observed  
127 axially at 50%, followed by  $3.23 \pm 0.11$  mm at 75% and the least fibre length of  $2.28 \pm 0.25$  mm was  
128 observed at 75% disc level. Samples collected from bamboo stands three (3) had the highest fibre length  
129 of  $3.25 \pm 0.15$  mm, followed by  $3.06 \pm 0.07$  mm of bamboo stand three (3) while the least  $2.28 \pm 0.25$  mm  
130 was recorded in *Bambusa-B. vulgaris* stands two (Table 1). It was observed that there was an increase in  
131 the fibre length in the radial position from the core section to the peripheral section.

132 The mean fibre length of  $3.25 \pm 0.15$  mm observed in this study was higher than  $1.63 \pm 0.50$  mm  
133 reported by Egbewole, *et al.*, 2015 for *Saccharum officinarum* and above 2.7 mm reported by (Atchison,  
134 1987) on fibre lengths of selected softwoods. It is also higher to the minimum 0.7 mm -1.6 mm value for  
135 hardwood fibre sources and to 1.7 mm values reported by Noah (2009) for bagasse fibres. Fibre length  
136 has been considered as a critical factor to be considered in selecting any species for the production of

**Comment [a2]:** After first "*Bambusa vulgaris*" write all others as "*B. vulgaris*"

**Formatted:** Font: Italic

**Formatted:** Font: Italic

137 high quality pulp for paper making (Dinwoodie, 1965). The long fibre length of bamboo is characterized by  
 138 high degree of opacity; stiffness and smoothness which are very suitable for making bank notes which  
 139 can withstand rough handling (Noah, 2009).  
 140 The result of the analysis of variance shows that the fibre length in radial (core and peripheral) position  
 141 differ significantly ( $p < 0.05$ ) but that of axial position (75%, 50% and 25%) does not have significant effects  
 142 on the fibre length of the fibre examined (Table 2). However, there is significant difference in the  
 143 interaction between the two position (axial and radial position), axial positioning and bamboo stands, the  
 144 three way interactions (radial position\* bamboo stands\*axial position), whereas, the interaction between  
 145 radial position and bamboo stands does not have significant difference on the fibre length of bamboo  
 146 examined. This thus indicates that the effects of radial position of the fiber length are independent of the  
 147 radial position between the fibres of the bamboo stands.

148 **Table 1: Mean value for Fibre length of *Bambusa B. vulgaris* in relation to sampling**  
 149 **height and radial position**

	Sampling height (%)	Radial Positioning	Bamboo Stand	Mean
FIBRE LENGTH	75	Core	B <sub>1</sub>	2.66 ± 0.10
			B <sub>2</sub>	2.34 ± 0.10
			B <sub>3</sub>	2.94 ± 0.28
		Peripheral	B <sub>1</sub>	2.97 ± 0.16
			B <sub>2</sub>	2.28 ± 0.25
			B <sub>3</sub>	2.73 ± 0.11
	50	Core	B <sub>1</sub>	2.45 ± 0.09
			B <sub>2</sub>	2.51 ± 0.14
			B <sub>3</sub>	3.06 ± 0.07
		Peripheral	B <sub>1</sub>	2.87 ± 0.12
			B <sub>2</sub>	2.72 ± 0.24
			B <sub>3</sub>	3.25 ± 0.15
25	Core	B <sub>1</sub>	2.65 ± 0.22	
		B <sub>2</sub>	2.36 ± 0.31	
		B <sub>3</sub>	2.95 ± 0.04	
	Peripheral	B <sub>1</sub>	2.67 ± 0.09	
		B <sub>2</sub>	2.80 ± 0.08	
		B <sub>3</sub>	3.23 ± 0.11	

150

151 **Table 2: Analysis of Variance (ANOVA) on Fibre length of *B. vulgaris***

SV	SS	DF	MS	F
RP	0.37	1	0.37	16.82*
AP	0.26	2	0.13	5.81 <sup>ns</sup>
BS	1.72	2	0.86	37.74*
RP * AP	0.16	2	0.08	3.46 <sup>ns</sup>
RP * BS	0.57	2	0.03	1.25 <sup>ns</sup>
AP * BS	0.56	4	0.14	6.11*
RP * AP * BS	0.28	4	0.07	3.04*
Error	0.82	36	0.03	
Total	4.21	53		

152 \*=Significant at 5% probability level ( $P \leq 0.05$ ); ns= not Significant ( $P \geq 0.05$ )

153

154 **Lumen Width of *Bambusa vulgaris***

155 The mean fibre length was presented in Table 3 below. The results revealed that the mean lumen width  
 156 ranged between  $3.52 \times 10^{-3} \mu\text{m}$  to  $4.46 \times 10^{-3} \mu\text{m}$  in the radial direction from the core to the peripheral  
 157 (bark) of the bamboo. The values increase along the axial direction from top (75%) to the base of the  
 158 bamboo stands (25%) and from the core to the peripheral (radial position). The pattern of variation  
 159 observed from the results also shows some form of inconsistency as the value decrease from the core to  
 160 the peripheral and along the sampling height. This finding is in accordance with Monteoliva, (2005). The  
 161 mean value observed was lower than the values observed on *Sterculia setigera* by Oluwadare and  
 162 Egbewole (2008).

163 The result of analysis of variance (ANOVA) on the lumen width is presented in table 4. The result shows  
 164 that there is significant difference among the bamboo stands, lumen width of the fibre in the radial  
 165 position, axial position (sampling height), whereas, there is no significance difference in the two way  
 166 interaction (BS\*AP and BS\*RP) and the three way interactions (BS \* AP \* RP) respectively.

167

168 **Table 3: Mean value for Lumen Width of *Bambusa vulgaris* in relation to sampling height**  
 169 **and radial position**

	Sampling height (%)	Radial Positioning	Bamboo Stands	Mean ( $\mu\text{m}$ )
<b>LUMEN WIDTH</b>	75	Core	B <sub>1</sub>	4.01 ± 0.34
			B <sub>2</sub>	3.77 ± 2.39
			B <sub>3</sub>	6.48 ± 0.12
		Peripheral	B <sub>1</sub>	6.83 ± 1.17
			B <sub>2</sub>	6.37 ± 0.29
			B <sub>3</sub>	6.53 ± 0.34
	50	Core	B <sub>1</sub>	5.97 ± 0.49
			B <sub>2</sub>	6.43 ± 0.77
			B <sub>3</sub>	7.31 ± 1.22
		Peripheral	B <sub>1</sub>	6.83 ± 0.40
			B <sub>2</sub>	6.89 ± 0.26
			B <sub>3</sub>	7.34 ± 0.52
	25	Core	B <sub>1</sub>	6.67 ± 1.91
			B <sub>2</sub>	6.69 ± 0.45
			B <sub>3</sub>	7.05 ± 0.41
Peripheral		B <sub>1</sub>	6.35 ± 0.54	
		B <sub>2</sub>	6.94 ± 0.42	
		B <sub>3</sub>	6.75 ± 0.31	

170  
 171  
 172  
 173  
 174  
 175  
 176  
 177  
 178  
 179  
 180  
 181  
 182  
 183  
 184  
 185  
 186  
 187  
 188



189 **Table 4: Analysis of Variance (ANOVA) on Lumen Width of *B. vulgaris***

SV	SS	DF	MS	F
BS	7.04	2	3.52	6.42*
AP	14.63	2	7.32	13.35*
RP	6.92	1	6.92	12.62*
BS * AP	2.9	4	0.72	1.32 <sup>ns</sup>
BS * RP	4.22	2	2.11	3.85 <sup>ns</sup>
AP * RP	9.06	2	4.53	8.26*
BS * AP * RP	3.74	4	0.94	1.71 <sup>ns</sup>
Error	19.74	36	0.55	
Corrected Total	68.24	53		

190 \*=Significant at 5% probability level ( $P \leq 0.05$ ); ns= not Significant ( $P \geq 0.05$ )

191

192 **Fibre Diameter of *Bambusa vulgaris***

193 The result obtained for mean values of Fiber diameter along the bamboo height (along stem) i.e. from top  
 194 to base for the three stands of bamboo is presented in Table 5 below. The mean values ranged from 3.52  
 195  $\mu\text{m}$  to 7.02  $\mu\text{m}$ , 3.58 to 4.41  $\mu\text{m}$  and 3.44  $\mu\text{m}$  to 4.36  $\mu\text{m}$  across the three (3) bamboo stands, sampling  
 196 height and radial direction sampling respectively. Among the sampling height, the sampling collected from  
 197 the middle which represent the 50% of the sampling height have higher fibre diameter at the peripheral  
 198 region compare to others. Whereas, the least fibre diameter (3.44  $\mu\text{m}$ ) was recorded at the base  
 199 (representing the 25% of the total height) and this is from the core region of the sample.

200 The highest mean fibre diameter value gotten from the study,(7.02  $\mu\text{m}$ ) falls below the range of 20- 40  $\mu\text{m}$   
 201 fibre diameter for hardwood fibres as reported by Usta and Eroghe, (1987), it is also at a distance range  
 202 to the 20.0  $\mu\text{m}$  fibre diameter in baggase as reported by Noah (2009) and 20.78  $\mu\text{m}$  by Egbewole, *et al.*,  
 203 2015 for *Saccharum officinarum*. This is lower than the observed trend reported by Ogunsanwo and  
 204 Onilude (2000) on *Triplochiton scleroxylon*.

205 The result of analysis of variance (ANOVA) on the Fibre diameter is presented in table 6. The result  
 206 shows that there is significant difference among the bamboo stands, with no significance difference in the  
 207 radial position and axial position (sampling height). Whereas, there are significance difference in the two  
 208 ways interactions (BS\*AP and BS\*RP) and the three ways interactions (BS \* AP \* RP) respectively of the  
 209 fibre diameter assessed.

210 **Table 5: Mean value for Fibre Diameter of *Bambusa vulgaris* in relation to sampling**  
 211 **height and radial position**

FIBRE DIAMETER	Sampling Height (%)	Radial Positioning	Bamboo Stands	Mean
		75	Core	B1
B2				4.3 ± 0.13
B3				3.52 ± 0.30
Peripheral			B1	4.28 ± 0.17
			B2	4.11 ± 0.22
			B3	3.82 ± 0.44
50		Core	B1	3.79 ± 0.21
			B2	3.58 ± 0.32
			B3	3.77 ± 0.67
		Peripheral	B1	4.3 ± 0.17
			B2	4.11 ± 0.53
			B3	4.41 ± 0.37
25		Core	B1	3.44 ± 0.28
			B2	3.47 ± 0.08
			B3	4.11 ± 0.93
	Peripheral	B1	4.36 ± 0.25	
		B2	4.19 ± 0.37	
		B3	3.74 ± 0.28	

212  
 213  
 214  
 215  
 216  
 217  
 218  
 219  
 220  
 221

222 **Table 6: Analysis of Variance (ANOVA) on Fibre Diameter of *B. vulgaris***

SV	SS	DF	MS	F
BS	3.99	2	1.99	12.40*
AP	0.51	2	0.26	1.59ns
RP	0.55	1	0.55	3.45ns
BS * AP	14.33	4	3.58	22.27*
BS * RP	2.2	2	1.1	6.84*
AP * RP	4.93	2	2.47	15.33*
BS * AP * RP	5.37	4	1.34	8.35*
Error	5.79	36	0.16	
Corrected Total	37.68	53		

223 \*=Significant at 5% probability level ( $P \leq 0.05$ ); ns= not Significant ( $P \geq 0.05$ )

224

225 **CONCLUSION**

226 The axial and radial fibre characteristic of *B. vulgaris* was successfully carried out in this study. Fiber  
 227 characteristics such as fibre length, fiber diameter and lumen width along the stem (sampling height) and  
 228 across the stem (radial position) for the three (3) bamboo stands examined. It was observed that there  
 229 was an increase in the fibre length in the radial position from the core section to the peripheral (back)  
 230 section. Along the length of the fibre of the bamboo stands examined (sampling height), there was an  
 231 inconsistency in the pattern of the variation of the fibre length from 75% to 25% sampling height which  
 232 could be as a result of environmental factor of the growing site and age of the bamboo stands. Along the  
 233 length of the fibre of the bamboo stands examined (axial position), there was an inconsistency in the  
 234 pattern of the variation of the fibre length from 75% to 25% sampling height which may be as a result of  
 235 environmental factor such as growing site and age of the bamboo stands.

236 Among the sampling height, the fibre collected from the middle which represent the 50% of the sampling  
237 height have higher fibre diameter at the peripheral region compare to others. Whereas, the least fibre  
238 diameter was recorded at the base (representing the 25% of the total height) and this is from the core  
239 region of the sample. It was also indicted generally that, the highest mean value of lumen width was  
240 found at the middle of the bamboo stem inward. This range also indicates the inconsistency in the lumen  
241 width of the fibre assessed.

## 242 REFERENCES

- 243 Bowyer, J., Fernholz, K., Frank, M., Howe, J., Bratkovich, S., Pepke, Ed.. Bamboo Products and  
244 their Environmental Impacts: Revisited 2014
- 245 Dinesh, B., Nagarnaik, P. B, Parbat, D. K., Waghe, U. P. Physical and Mechanical Properties of  
246 Bamboo (*Dendrocalamus Strictus*). 2014: 5(1). *International Journal of Scientific & Engineering*  
247 *Research*, Volume
- 248 Egbewole Z. T., Omoake, P. O. and Rotowa O. J. Fibre Quality Assessment of *Saccharum*  
249 *officinarum* (Sugarcane) Bagasse as a raw material for pulp and paper production. 2015; 5(1):  
250 57-65. *NSUK Journal of Science and Technology (NJST)*. Publication of Nasarawa State  
251 University, Keffi.
- 252 Gritsch, C. S., Kleist, G. and Murphy, R. Developmental changes in cell wall structure of phloem  
253 fibres of the bamboo *Dendrocalamus asper*. 2004: 94, 497–505. *Ann. Bot.*.
- 254 Itoh, T. Lignification of bamboo (*Phyllostachys heterocycla* Mitf.) during its growth.  
255 *Holzforschung*. 1990: 44, 191–200.
- 256 Lobovikov, M., Paudel, S., Piazza, M., Ren, H., and Wu, J.. Bamboo Products and Trade–  
257 Bamboo Product Statistics. 2007: 18, 31-38. In: INBAR/UN FAO, World Bamboo Resources, –  
258 *Non-Wood Forest Products*.
- 259 Murphy, R. J. and Alvin, K. L.. Variation in fibre wall structure in bamboo. 1992; 13, 403–410;  
260 *IAWA Bulletin*.

261 Ogunsanwo, Y.O., Onilude, M. A.. Radial and Vertical Variation in Fibre Characteristics of  
262 Plantation Grown Obeche. 2000; 30 (2): 33-37. *Nigeria. Journal of Forestry*..

263 Oluwadare, A. O. and Egbewole, Z. T. Wood Quality Studies in Plantation Grown Sterculia  
264 (*Steculia setigera*) in the Guinea Savannah, Nigeria. 2008; 2: 22-33. *Research Journal of*  
265 *Forestry*.

266 Parameswaran, N. and Liese, W.. Fine structure of bamboo fibres. 1976; 10, 231–246. *Wood*  
267 *Science. Technology*..

268 Suzuki, K. and Itoh, T.. The changes in cell wall architecture during lignification of bamboo,  
269 *Phyllostachys aurea* Carr. *Trees* 2001; 15, 137–147.

270 Zobel B. J. and van Buijtenen J. P. *In Wood Variation: Its Causes and Control*. ed Timell TE  
271 (Springer-Verlag, Heidelberg). 1989.

272 Yu, Y., Jiang, Z., Fei, B., Wang, G. and Wang, H.. An improved microtensile technique for  
273 mechanical characterization of short plant fibres: a case study on bamboo fibres .2011; 46,  
274 739–746.. *Journal Material Science*.

275 Zou, L., Jin, H., Lu, W. Y. and Li, X.. Nanoscale structural and mechanical characterization of  
276 the cell wall of bamboo fibers. 2009; 29, 1375–1379. *Materials Sci. Eng. C*.