

AXIAL AND RADIAL VARIATION OF FIBRE CHARACTERISTICS OF *Bambusa vulgaris*

ABSTRACT

This study was carried out to investigate the axial and radial variation of fibre characteristics of *Bambusa vulgaris*. There were eighteen treatments for both axial and radial variation. The treatments were replicated three (3) times, in Complete Randomized Design (CRD). This study was carried out at the Wood Anatomy Laboratory of the Department of Forest Product Development and Utilization, Forestry Research Institute of Nigeria, Ibadan. Three (3) stands of *B. vulgaris* stands were randomly selected. Samples were cut into 10cm discs collected at 25%, 50% and 75% of the total height (axial positioning) of the bamboo stems. The samples discs were partitioned into two zones which are core and peripheral (bark) layers. From each of the disc, 3 slivers were obtained both from radial and axial positions. Slivers obtained were macerated with an equal volume (1:1) of 10% glacial Acetic acid and 30% Hydrogen Peroxide (H₂O₂) at 100 ±2 °C. The resulting image on light microscope screen was measured for fibre length, fibre diameter and lumen width.

At 50% sampling height and at outer layer, the highest fibre length of 3.25 mm, followed by 3.06 mm of bamboo stand three (3) while the least 2.28 mm was recorded in stands two (2) of 75% axial positioning and at peripheral layer. The lumen width ranged between 3.52 × 10⁻³ μm to 4.46 × 10⁻³ μm in the radial direction from the core to the peripheral (bark) of the bamboo. The result obtained for mean values of fiber diameter along the bamboo height ranged from 3.53 × 10⁻³ μm to 4.46 × 10⁻³ μm across the three (3) bamboo stands, sampling height and radial direction sampling respectively.

26 Among the fibre positioning, the fibre collected from 50% of the sampling height have higher
27 fibre diameter, lumen width and fibre diameter at the peripheral region compare to the others.

28 **KEYWORDS:** *Bambusa vulgaris*, Fibre length, Fibre diameter and Lumen width.

29

30 **INTRODUCTION**

31 Fibre characteristics are related to many structural, physical and chemical properties of wood. The fibre
32 characteristics includes fibre diameter, fibre length and lumen width. It affects many woody-products
33 manufacturing, like pulping process, the behavior in the drying process and the behavior to cutting and
34 machining, the variations in fibre dimensions/characteristics are also present in the tree's radial,
35 longitudinal direction and within the annual rings (Zobel and Van Buijtenen, 1989). The variation may be
36 due to genetic, physiological or silvicultural treatment

37 In general, fibers can be classified into three categories: wood, non-wood, and non-plant. The term “non-
38 wood” was developed to distinguish plant fibers from the two main sources of wood fibers; hardwoods
39 and softwoods. Non-wood or agro-based fibers are derived from selected tissues of various mono or
40 dicotyledonous plants and are categorized botanically as grass, blast, leaf, or fruit fibers. Some non-wood
41 fibers are classified by means of type of production; fibers such as sugar cane bagasse, wheat straw and
42 corn stalks are byproducts. Other non wood fibers are grouped as “fiber plants,” plants with high cellulose
43 content that are cultivated primarily for the sake of their fibers such as jute, kenaf, flax, cotton, and ramie.
44 Non-wood fibers can be used to make paper, although the quality depends on the source of the fibers.

45 *B. vulgaris* (A bamboo species) has been considered as one of the fastest growing plants in the world.
46 Bamboo has social, economic and cultural significance and is used extensively for building materials
47 along with thousands of uses. It is highly versatile raw material for different works. The bamboo is
48 lightweight, flexible, tough, high tensile, cheap material than the other building materials like steel.
49 Bamboo can be used in various building works. Bamboo structures are reported to be flexible, earthquake
50 resistant, lightweight and cheap. Bamboo can be used as reinforcement in various structural members.
51 Bamboo is a green material for sustainable development and has various advantages. The use of
52 bamboo may be promoted for green buildings and sustainable development (Dinesh *et al.*, 2014). In fact,
53 bamboo culture has been described as an essential part of human history and civilization, especially in
54 Asia (Lobovikov *et al.*, 2007).

55 In addition, bamboo is used for scaffolding in construction projects often to great heights. While bamboo
56 continues to be used in these traditional ways, it has also become an important raw material for
57 production of modern building products (Bowyer *et al.*, 2014)

58 Fibres have been regarded as one of the main components that determine the mechanical properties of
59 any woody materials including bamboo, owing to their unidirectional arrangement in the tissue as well as
60 their unique cell wall structure (Gritsch *et al.*, 2004).

61 Many studies have been done regarding bamboo; Fibre wall anatomy (Parameswaran and Liese, 1976),
62 and in particular cell wall thickening (Murphy and Alvin, 1997; Gritsch *et al.*, 2004) lignification (Itoh, 1990;
63 Lybeer and Koch, 2005) and cell wall nano-structural changes (Suzuki and Itoh, 2001) during
64 development of bamboo culms, mechanical properties of fibres or fibre caps (Zou *et al.*, 2009 and Yu *et*
65 *al.*, 2011), and the underlying structure–property relationships of bamboo fibres that establish the
66 gradients across the fibre caps have been intensively studied, but there has been little information on
67 fibre characteristics variation along axial (top, middle and bottom and radial (bark and core) dimension in
68 relations to its pulping potentials. Therefore, this study sought to provide information in this regards on
69 variations across (radial) and along (axial) axis of *B. vulgaris*.

70

71 **MATERIALS AND METHODS**

72 **Materials**

73 The materials used for determining the variation in the fibre characteristics of *B. vulgaris* from the same
74 location are; test tubes, tube rack, acetic acid (CH₃COOH), Hydrogen peroxide (H₂O₂), Spatula, Beaker,
75 Distilled water, Light microscope, saw, sharp knife, nose cover and hand glove.

76 **Sample Area**

77 The *B. vulgaris* stands used for this experiment was collected from Forestry Research Institute of Nigeria
78 (FRIN), Ibadan, Oyo State. The institute is lies between Latitude 07°22' N and Longitude 03°58' E (Map of
79 the World, 2017) of the Greenwich meridian. It is characterized by mean annual rainfall of 1400-1500 mm,
80 while the mean annual temperature is 26.46 °C. The average relative humidity is 80-85% (FRIN, 2017).

81

82 **Experimental Site**

83 The experiment was carried out at Wood Anatomy laboratory, Department of Forest Products
84 Development and Utilization (FPD&U), Forestry Research Institute of Nigeria, Ibadan (FRIN).

85 **Sampling Technique**

86 For this study, three (3) stands of *B. vulgaris* were randomly selected from the bamboo plantation, behind
87 horticultural nursery, Forestry Research Institute of Nigeria, Ibadan (FRIN) and harvested. Samples were
88 cut into 10 cm height collected at 25%, 50% and 75% of the total height (axial positions) of the bamboo
89 stems. The samples discs were later partitioned into two zones (radial positioning) which are core and
90 peripheral (bark) layers.

91

92 **Sample Preparation**

93 *B. vulgaris* discs of size 10 cm collected were collected at 25%, 50% and 75% (which represent bottom,
94 middle and top of the three (3) stands respectively). Three (3) slivers each were also obtained from radial
95 positioning (Core and peripheral layers) from each bamboo stem. Bamboo slivers obtained were put into
96 test tubes and macerated with an equal volume (1:1) of 10% glacial Acetic acid and 30% Hydrogen
97 Peroxide (H_2O_2) at 100 ± 2 °C and boiled until soft and bleached white. The slivers were then washed,
98 placed in 30 mL-test tubes with 20 mL-distilled water and shaken vigorously to separate the fibre bundles
99 into individual fibres. The macerated fibres suspension was carefully aligned on a slide using white tread.
100 The resulting image on light microscope screen was measured for fibre length, fibre diameter and lumen
101 width.

102 **Microscopy**

103 The separated fibres per samples in each test tube were mounted on microscope slide and examined
104 under a Riechert microscope with a tracer reflector. The magnified and transparent fibres were projected
105 by the tracer reflector on which the fibres were viewed and traced under magnification $\times 10$. Few fibres
106 were measured with calibration on the eye piece.

107 **Parameters Determined**

108 The following parameters were determined:

- 109 • **Fibre length of the sample:** It was measured using the microscope by aligning fibre length of the
110 chip sideway to the graduated ruler in the microscope;

- 111 • **Fibre diameter of the sample:** this was measured by placing the graduated ruler in the
112 microscope in horizontal direction at the middle of the fibre;
- 113 • **Lumen width of the sample:** This is the width of the inner space.

114 **Data analysis**

115 The data collected were analyzed using $3 \times 3 \times 2$ factorial experiments in a Completely Randomized
116 Design (CRD). Each treatment was replicated 3 times making 54 observations. The data gotten from the
117 experiment was subjected to Analysis of Variance (ANOVA). The follow up test was conducted to obtain
118 the difference between the means using the Duncan Multiple Range Test (DMRT) at 5% probability
119 levels.

120 **RESULTS AND DISCUSSION**

121 **Fibre Length of *B. vulgaris***

122 The average fibre length was presented in Table 1. The longest fibre length of 3.25 ± 0.15 mm was
123 observed axially at 50% height, followed by 3.23 ± 0.11 mm at 75% height and the least fibre length of
124 2.28 ± 0.25 mm was observed at 75% height disc level. Samples collected from bamboo stands three (3)
125 had the highest fibre length of 3.25 ± 0.15 mm, followed by 3.06 ± 0.07 mm of bamboo stand three (3) while
126 the least 2.28 ± 0.25 mm was recorded in *B.vulgaris* stands two (Table 1). It was observed that there was
127 an increase in the fibre length in the radial position from the core section to the peripheral section (bark).

128 The average fibre length (FL) of 3.25 ± 0.15 mm observed in this study is lower compared to the work of
129 Sharma *et al* (2014) who reported 3.65 mm for *Bambusa bambus* (5.62mm) from middle to top sampling,
130 whereas, the results (fibre length) corroborate the work of Omobowale and Ogedengbe (2008) who
131 reported fibre length 2.8 mm to 3.7 mm from base to the top in Nigeria *B. vulgaris*. The FL values
132 examined in this study is higher than 1.63 ± 0.50 mm reported by Egbewole *et al.* (2015) on non-wood fibre
133 of *Saccharum officinarum* and above 2.7 mm reported by (Atchison, 1997) on fibre lengths of selected
134 softwoods. It is also higher to the minimum 0.7 mm -1.6 mm value for hardwood fibre sources and to 1.7
135 mm values reported by Noah (2009) for bagasse fibres. An increasing trend of fibre length was evidenced
136 across the width of the culms examined.

137 The result of the analysis of variance shows that the fibre length in radial position (core and peripheral)
 138 differ significantly ($p < 0.05$) but that of axial position (75%, 50% and 25%) does not have significant effects
 139 on the fibre length of the fibre examined (Table 2).

140 However, there is significant difference in the interaction between the two position (axial and radial), axial
 141 positioning and bamboo stands, the three way interactions (radial position* bamboo stands*axial
 142 position), whereas, the interaction between radial position and bamboo stands does not have significant
 143 difference on the fibre length of bamboo examined. Thus, this indicates that the effects of radial position
 144 of the fiber length are independent of the fibers radial position between the fibres of the bamboo stands.

145
 146 **Table 1: Average value of *B. vulgaris* fibre length in relation to sampling height and radial**
 147 **position**

	Sampling height (%)	Radial Positioning	Bamboo Stand	Average (mm)	
FIBRE LENGHT	75	Core	B ₁	2.66 ± 0.10	
			B ₂	2.34 ± 0.10	
			B ₃	2.94 ± 0.28	
		Peripheral	B ₁	2.97 ± 0.16	
			B ₂	2.28 ± 0.25	
			B ₃	2.73 ± 0.11	
		50	Core	B ₁	2.45 ± 0.09
				B ₂	2.51 ± 0.14
				B ₃	3.06 ± 0.07
	Peripheral		B ₁	2.87 ± 0.12	
			B ₂	2.72 ± 0.24	
			B ₃	3.25 ± 0.15	
	25	Core	B ₁	2.65 ± 0.22	
			B ₂	2.36 ± 0.31	
			B ₃	2.95 ± 0.04	
Peripheral		B ₁	2.67 ± 0.09		
		B ₂	2.80 ± 0.08		
		B ₃	3.23 ± 0.11		

148

149

150

151

152

153
154

Table 2: Analysis of Variance (ANOVA) of *B. vulgaris* fibre length

SV	SS	DF	MS	F
RP	0.37	1	0.37	16.82*
AP	0.26	2	0.13	5.81 ^{ns}
BS	1.72	2	0.86	37.74*
RP * AP	0.16	2	0.08	3.46 ^{ns}
RP * BS	0.57	2	0.03	1.25 ^{ns}
AP * BS	0.56	4	0.14	6.11*
RP * AP * BS	0.28	4	0.07	3.04*
Error	0.82	36	0.03	
Total	4.21	53		

155 *=Significant at 5% probability level ($P \leq 0.05$); ns= not Significant ($P \geq 0.05$)

156 BS=Bamboo stands; AP=Axial Positions; and RP=Radial Positions

157

158 **Fibre Lumen Width of *B. vulgaris***

159 The average fibre lumen width was presented in Table 3. The results revealed that the average lumen
160 width ranged between $3.52 \times 10^{-3} \mu\text{m}$ to $4.46 \times 10^{-3} \mu\text{m}$ in the radial direction from the core to the
161 peripheral (bark) of the bamboo. The values increase along the axial direction from top (75%) to the
162 bottom of the bamboo stands (25%) and from the core to the peripheral (radial position). The pattern of
163 variation observed from the results also shows some form of inconsistency as the value decrease from
164 the core to the peripheral and along the sampling height. However, this finding is in accordance with
165 Monteoliva, (2005).

166 The average value observed in this study ($4.46 \mu\text{m}$) was higher than the *B.vulgaris* fiber lumen diameter
167 ($2.3 \mu\text{m}$ - $2.6 \mu\text{m}$) reported by Razak *et al* (2010), .and findings of Lessard & Chouinard (1980) who
168 reported fibre lumen diameter $4.0 \mu\text{m}$, $3.98 \mu\text{m}$ in, Philippine and India *B. vulgaris* respectively. However,

169 the values is lower to findings of Sharma *et al* (2014) on *B. bamboos* (24.96 μm) and 23 μm - 37 μm
 170 reported by Abd Latif *et al*, (1993) on *B. bluemiana*.

171 The result of analysis of variance (ANOVA) on the lumen width is presented in Table 4. The result shows
 172 that there is significant difference among the bamboo stands, lumen width of the fibre in the radial
 173 position, axial position (sampling height), whereas, there is no significance difference in the two way
 174 interaction (BS*AP and BS*RP) and the three way interactions (BS * AP * RP), respectively.

175
 176 **Table 3: Average value for Lumen Width of *B. vulgaris* in relation to sampling height and**
 177 **radial position**

	Sampling height (%)	Radial Positioning	Bamboo Stands	Mean (μm)
LUMEN WIDTH	75	Core	B ₁	4.01 \pm 0.34
			B ₂	3.77 \pm 2.39
			B ₃	6.48 \pm 0.12
		Peripheral	B ₁	6.83 \pm 1.17
			B ₂	6.37 \pm 0.29
			B ₃	6.53 \pm 0.34
	50	Core	B ₁	5.97 \pm 0.49
			B ₂	6.43 \pm 0.77
			B ₃	7.31 \pm 1.22
		Peripheral	B ₁	6.83 \pm 0.40
			B ₂	6.89 \pm 0.26
			B ₃	7.34 \pm 0.52
	25	Core	B ₁	6.67 \pm 1.91
			B ₂	6.69 \pm 0.45
			B ₃	7.05 \pm 0.41
Peripheral		B ₁	6.35 \pm 0.54	
		B ₂	6.94 \pm 0.42	
		B ₃	6.75 \pm 0.31	

178
 179
 180
 181
 182
 183
 184
 185
 186

187 **Table 4: Analysis of Variance (ANOVA) on Lumen Width of *B. vulgaris***

SV	SS	DF	MS	F
BS	7.04	2	3.52	6.42*
AP	14.63	2	7.32	13.35*
RP	6.92	1	6.92	12.62*
BS * AP	2.9	4	0.72	1.32 ^{ns}
BS * RP	4.22	2	2.11	3.85 ^{ns}
AP * RP	9.06	2	4.53	8.26*
BS * AP * RP	3.74	4	0.94	1.71 ^{ns}
Error	19.74	36	0.55	
Corrected Total	68.24	53		

188 ***=Significant at 5% probability level ($P \leq 0.05$); ns= not Significant ($P \geq 0.05$)**

189 **BS=Bamboo stands; AP=Axial Positions; and RP=Radial Positions**

190

191 **Fibre Diameter of *B. vulgaris***

192 The result obtained for average values of fiber diameter along the bamboo height (along stem) i.e. from
 193 top to bottom for the three stands of bamboo is presented in Table 5. The average values ranged from
 194 3.52 μm to 7.02 μm , 3.58 to 4.41 μm and 3.44 μm to 4.36 μm across the three (3) bamboo stands,
 195 sampling height and radial direction specimens respectively. Among the sampling height, the specimens
 196 collected from the middle that represent the 50% of the sampling height have higher fibre diameter at the
 197 peripheral region compare to others. Whereas, the least fibre diameter (3.44 μm) was recorded at the
 198 bottom (representing the 25% of the total height) and this was obtained from the core region of the
 199 sample.

200 The result shows that the fibre lumen diameter are smaller and lower for region of base to top compare to
 201 result obtained on *Dindrocalamus strictus* (13.37 μm) by Sharma *et al* (2014) It is also at a distance
 202 range to the 20.0 μm fibre diameter in *Saccharum officinarum* as reported by Noah (2009). This is lower
 203 than the observed trend reported by Ogunsanwo and Onilude (2000) on *Triplochiton scleroxylon*.

204 The result of analysis of variance (ANOVA) on the fibre diameter is presented in Table 6. The result
 205 shows that there is significant difference among the bamboo stands, with no significance difference in the
 206 radial position and axial position (sampling height). Whereas, there are significant difference in the two
 207 ways interactions (BS*AP and BS*RP) and the three ways interactions (BS * AP * RP), respectively, of
 208 the fibre diameter assessed.

209 **Table 5: Mean value for Fibre Diameter of *B. vulgaris* in relation to sampling height and**
 210 **radial position**

FIBRE DIAMETER	Sampling Height (%)	Radial Positioning	Bamboo Stands	Mean μm
			Core	B1
			B2	4.3 \pm 0.13
	75		B3	3.52 \pm 0.30
		Peripheral	B1	4.28 \pm 0.17
			B2	4.11 \pm 0.22
			B3	3.82 \pm 0.44
		Core	B1	3.79 \pm 0.21
			B2	3.58 \pm 0.32
	50		B3	3.77 \pm 0.67
		Peripheral	B1	4.3 \pm 0.17
			B2	4.11 \pm 0.53
			B3	4.41 \pm 0.37
		Core	B1	3.44 \pm 0.28
			B2	3.47 \pm 0.08
	25		B3	4.11 \pm 0.93
		Peripheral	B1	4.36 \pm 0.25
			B2	4.19 \pm 0.37
			B3	3.74 \pm 0.28

211
 212
 213
 214
 215
 216
 217
 218
 219
 220

221
222
223
224

Table 6: Analysis of Variance (ANOVA) on fibre diameter of *B. vulgaris*

SV	SS	DF	MS	F
BS	3.99	2	1.99	12.40*
AP	0.51	2	0.26	1.59ns
RP	0.55	1	0.55	3.45ns
BS * AP	14.33	4	3.58	22.27*
BS * RP	2.2	2	1.1	6.84*
AP * RP	4.93	2	2.47	15.33*
BS * AP * RP	5.37	4	1.34	8.35*
Error	5.79	36	0.16	
Corrected Total	37.68	53		

225 *=Significant at 5% probability level ($P \leq 0.05$); ns= not Significant ($P \geq 0.05$)
226 **BS=Bamboo stands; AP=Axial Positions; and RP=Radial Positions**

227
228

229 CONCLUSION

230 The axial and radial fibre characteristics of *B. vulgaris* was successfully carried out in this study. Fiber
231 characteristics such as fibre length, fiber diameter and lumen width along the stem (sampling height) and
232 across the stem (radial position) for the three (3) bamboo stands were examined. It was observed that
233 there was an increase in the fibre length in the radial position from the core section to the peripheral
234 (bark) section. Along the length of the fibre of the bamboo stands examined (sampling height), there was
235 an inconsistency in the pattern of the variation of the fibre length from 75% to 25% sampling height which
236 could be as a result of differences in the age of the bamboo stands harvested for the study and the

237 ecological zone of extraction when compared the results to same and other species from other region.
238 Along the length of the fibre of the bamboo stands examined (axial position), there was an inconsistency
239 in the pattern of the variation of the fibre length from 75% to 25% sampling height which may be as a
240 result of age of the bamboo stands.

241 Among the sampling height, the fibre collected from the middle that represent the 50% of the sampling
242 height have higher fibre diameter at the peripheral region compare to others. Whereas, the least fibre
243 diameter was recorded at the bottom (representing the 25% of the total height) and this is from the core
244 region of the sample. It was also noted generally that, the highest mean value of lumen width was found
245 at the middle of the bamboo stem inward.

246 The fibre length of *B. vulgaris* used for this study fall within short fibre cellulosic materials. The Axial
247 sampling of *B. vulgaris* showed no significant differences in the fibre qualities examined at any height of
248 the bamboo stems except on lumen width. This is indicating that the bamboo possesses good pulping
249 qualities suitable for pulp and paper production at any point of fibre collection (axial and radial positions).

250

251 REFERENCES

252 Abd.Latif, M., Ashaari, A., Jamaludin K., and J. Mohd. Z. Effects of anatomical characteristics on
253 the physical and mechanical properties of *Bambusa blumeana*. 1993; *Journal of Tropical*
254 *Forest Science*. 6(2): 159-170.

255 Atchison, J. E. Data on non-wood plant fibers. In. Pulp and Paper Manufacture. Vol. 1.
256 Properties of fibrous raw materials and their preparation for pulping. (1997): M.J. Kocurek and
257 C.F.B. Stevens, Editors. CPPA., Montreal, Canada:157-169.

258 Bowyer, J., Fernholz, K., Frank, M., Howe, J., Bratkovich, S., Pepke, Ed. Bamboo Products and
259 their Environmental Impacts: Revisited 2014; Pp 1-17

260 Dinesh, B., Nagarnaik, P. B, Parbat, D. K., Waghe, U. P. Physical and Mechanical Properties of
261 Bamboo (*Dendrocalmus strictus*). 2014: 5(1). *International Journal of Scientific & Engineering*
262 *Research*, Volume 5, Issue 1.

263 Egbewole Z. T., Omoake, P. O. and Rotowa O. J. Fibre Quality Assessment of *Saccharum*
264 *officinarum* (Sugarcane) Bagasse as a raw material for pulp and paper production. 2015; 5(1):
265 57-65. *NSUK Journal of Science and Technology (NJST)*. Publication of Nasarawa State
266 University, Keffi.

267 Gritsch, C. S., Kleist, G. and Murphy, R. Developmental changes in cell wall structure of phloem
268 fibres of the bamboo *Dendrocalamus asper*. 2004: 94, 497–505. *Ann. Bot.*

269 Itoh, T. Lignification of bamboo (*Phyllostachys heterocycla* Mitf.) during its growth.
270 *Holzforschung*. 1990: 44, 191–200.

271 Lybeer, B. and Koch, G. A topochemical and semiquantitative study of the lignifications during
272 ageing of bamboo culms. 2005: (*Phyllostachys viridiglaucescens*). *IAWA J.* 26, 99–109.

273 Lobovikov, M., Paudel, S., Piazza, M., Ren, H., and Wu, J. Bamboo Products and Trade–
274 Bamboo Product Statistics. 2007: 18, 31-38. In: INBAR/UN FAO, World Bamboo Resources, –
275 *Non-Wood Forest Products*.

276 Monteoliva, E. A. Variation of wood density and fibre length in six willow clones (*Salix spp*).
277 2005: *IAWA Journal*, 26: 197-202

278 Murphy, R. J. and Alvin, K. L. Variation in fibre wall structure in bamboo. 1992; 13, 403–410;
279 *IAWA Bulletin*.

280 Noah, S. A. Fundamentals of Pulp and Paper Manufacture. Fasco Publishers. Ibadan. 2009;
281 Pp11-12.

282 Ogunsanwo Y.O., Onilude, M. A. Radial and Vertical Variation in Fibre Characteristics of
283 Plantation Grown Obeche. 2000; *Nigeria Journal of Forestry*, 30 (2): 33-37.

284 Omobowale, M.O, and Ogedengbe K., Trends in fiber characteristics of Nigerian grown bamboo
285 and its effect on its impact and tensile strengths. *Bamboo Science and Culture*: 2008; *The*
286 *Journal of the American Bamboo Society* 21(1): 9-13

287 Parameswaran, N. and Liese, W. Fine structure of bamboo fibres. 1976; 10, 231–246. *Wood*
288 *Science. Technology*.

289 Razak, W, Mohd Tamizi, M, Othman S., Aminuddin M., Affendy H., and Izyan, K. Anatomical and
290 Physical Properties of Cultivated Two- and Four-year-old *Bambusa vulgaris*. 2010; *Sains Malaysiana*
291 39(4): 571–579.

292 Sharma, P. K., Nath, S. K. and Murthy, N. Investigation on Fibre Characteristics of
293 *Dendrocalmus Strictus* and *Bambusa Bambos*. 2014; *International Journal of Engineering*
294 *Innovation & Research*. Volume 3, Issue 3, Pp 254-258.

295 Suzuki, K. and Itoh, T. The changes in cell wall architecture during lignification of bamboo,
296 *Phyllostachys aurea* Carr. **Trees 2001**; 15, 137–147.

297 Zobel B. J. and van Buijtenen J. P. In *Wood Variation: Its Causes and Control*. Ed. Timell TE
298 (Springer-Verlag, Heidelberg). 1989.

299 Yu, Y., Jiang, Z., Fei, B., Wang, G. and Wang, H.. An improved microtensile technique for
300 mechanical characterization of short plant fibres: a case study on bamboo fibres .2011; 46,
301 739–746. *Journal Material Science*.

302 Zou, L., Jin, H., Lu, W. Y. and Li, X. Nanoscale structural and mechanical characterization of the
303 cell wall of bamboo fibers. 2009; 29, 1375–1379. *Materials Sci. Eng. C*.